

INTRODUCTION OF PETROCHEMICAL PRODUCTS

LINEAR LOW DENSITY POLYETHYLENE (L.L.D.P.E)

LL 209 AA

FILMGRADE / AMIRKABIR, SHAHZAND, TABRIZ Pet.Co.

DATASHEET	VALUE	UNIT	TEST CONDITIONS	TEST METHOD
Density	0.921	g/cm ³	-----	ASTM D1505
MFI	0.9	g/10 min	At 2.16Kg, 190°C	ASTM D1238
Film Elongation at Break, MD	620	%	-----	ASTM D882
Film Elongation at Break, TD	840	%	-----	ASTM D882
Film Tensile Strength at Break, MD	41	MPa	-----	ASTM D882
Film Tensile Strength at Break, TD	32	MPa	-----	ASTM D882
Film Tensile Strength at Yield, MD	10	MPa	-----	ASTM D882
Film Tensile Strength at Yield, TD	11	MPa	-----	ASTM D882
Impact Strength, Dart	100	gr	Method A	ASTM D1709
Vicat Softening Point	105	°C	-----	ASTM D1525
Gloss	36	-----	45 °C	ASTM D2457
Haze	12	%	-----	ASTM D1003

- Manufacturer: Amirkabir, Shahzand and Tabriz Pet.co.
- Application: Film, Food Bag, Stretch Film, Heavy Duty Film, Agricultural Film, General Purpose Film, Liner Bag.
- Process: Film.
- Amirkabir Pet.co. Additives: Antioxidant, neutralizer.
- Shahzand and Tabriz Pet.co. Additives: Antioxidant.
- Features: Good sewability, good processability, good optical properties, food contact grade, good puncture resistance.

PETRO BAMDAD AZARAN

ENGINEERING & TRADING CO

Add: No.148, Motahari St., Tehran, Iran -- Tel: +98 21 87700799 -- Email/Web:

info@petrobam.com/www.petrobam.com