

INTRODUCTION OF PETROCHEMICAL PRODUCTS

POLYPROPYLENE - COPOLYMER (P.P)

HP 550J

PP HOMOPOLYMER / JAM Pet.Co.

DATASHEET	VALUE	UNIT	TEST CONDITIONS	TEST METHOD
Density	0.9	g/cm ³	-----	ASTM D1505
MFI	3.2	g/10 min	At 2.16Kg, 230°C	ASTM D1238
Flexural Modulus	1400	MPa	-----	ASTM D790
Izod Impact Strength, Notched	50	J/m	at 23°C,	ASTM D256
Tensile Elongation at Yield	9	%	-----	ASTM D638
Tensile Strength at Yield	32	MPa	-----	ASTM D638
Heat Deflection Temperature	84	°C	At 0.46 MPa	ASTM D648
Oven Aging	360	h	At 150°C , Air	ASTM D3012
Vicat Softening Point	152	°C	10 N	ASTM D1525

- Manufacturer: Jam Pet.co.
- Application: Carpets and rugs, belts, bags and backpacks, dairy product containers, sheets, artificial grass, fibers, thermoforming sheets, raffia, ropes and twine, monofilament fibers, brush fibers, tape, ribbon yarn, refrigerator parts.
- Process: Extrusion, Textile.
- Features: Good processability, good mechanical properties, food contact grade.

PETRO BAMDAD AZARAN
ENGINEERING & TRADING CO

Add: No.148, Motahari St., Tehran, Iran -- Tel: +98 21 87700799 -- Email/Web:
info@petrobam.com/www.petrobam.com