

# INTRODUCTION OF PETROCHEMICAL PRODUCTS

## POLYPROPYLENE - COPOLYMER (P.P)

# RG 1102XK

PP HOMOPOLYMER / REGAL Pet.Co.

DATASHEET	VALUE	UNIT	TEST CONDITIONS	TEST METHOD
Density	0.91	g/cm <sup>3</sup>	-----	ASTM D1505
MFI	4	g/10 min	At 2.16Kg, 230°C	ASTM D1238
Charpy Impact Notched	4	KJ/m2	at 23°C,	ISO 179/1eA
Charpy Impact Notched	1.7	KJ/m2	at -30°C,	ISO 179/1eA
Hardness Ball Indentation	74	MPa	-----	ISO 2039-1
Tensile Elongation at Yield	9	%	50 mm/min	ASTM D638
Tensile Modulus	1500	MPa	1 mm/min	ASTM D638
Tensile Strength at Yield	34	MPa	50 mm/min	ASTM D638
Heat Deflection Temperature	85	°C	At 0.46 MPa	ASTM D648
Melting Point	163	°C	DSC Analysis	ASTM D3417
Vicat Softening Point	154	°C	10 N	ASTM D1525

- Manufacturer: Regal Pet.co.
- Application: Fibers, Carpets and Rugs, Ribbon Yarn, Raffia.
- Process: Textile, Thermoforming.

**PETRO BAMDAD AZARAN**  
ENGINEERING & TRADING CO

Add: No.148, Motahari St., Tehran, Iran -- Tel: +98 21 87700799 -- Email/Web:  
info@petrobam.com/www.petrobam.com