

INTRODUCTION OF PETROCHEMICAL PRODUCTS

POLYPROPYLENE - COPOLYMER (P.P)

RG 1102XL

PP HOMOPOLYMER / REGAL Pet.Co.

DATASHEET	VALUE	UNIT	TEST CONDITIONS	TEST METHOD
Density	0.91	g/cm ³	-----	ASTM D1505
MFI	5.5	g/10 min	At 2.16Kg, 230°C	ASTM D1238
Charpy Impact Notched	3.5	KJ/m2	at 23°C,	ISO 179/1eA
Charpy Impact Notched	1.5	KJ/m2	at -30°C,	ISO 179/1eA
Hardness Ball Indentation	74	MPa	-----	ISO 2039-1
Tensile Elongation at Yield	9	%	50 mm/min	ASTM D638
Tensile Modulus	1500	MPa	1 mm/min	ASTM D638
Tensile Strength at Yield	34	MPa	50 mm/min	ASTM D638
Heat Deflection Temperature	85	°C	At 0.46 MPa	ASTM D648
Melting Point	163	°C	DSC Analysis	ASTM D3417
Vicat Softening Point	154	°C	10 N	ASTM D1525

- Manufacturer: Regal Pet.co.
- Application: Fibers, CF fibers, BCF fibers.
- Process: Textile.
- Features: Gas Fading Stabilized.

PETRO BAMDAD AZARAN
ENGINEERING & TRADING CO

Add: No.148, Motahari St., Tehran, Iran -- Tel: +98 21 87700799 -- Email/Web:
info@petrobam.com/www.petrobam.com