

# INTRODUCTION OF PETROCHEMICAL PRODUCTS

## POLYPROPYLENE - COPOLYMER (P.P)

# ZH 500M

PP HOMOPOLYMER / NAVID ZAR SHIMI Pet.Co.

DATASHEET	VALUE	UNIT	TEST CONDITIONS	TEST METHOD
Density	0.9	g/cm <sup>3</sup>	-----	ASTM D1505
MFI	7 - 11	g/10 min	At 2.16Kg, 230°C	ASTM D1238
Flexural Modulus	1400 - 1700	MPa	-----	ASTM D790
Hardness, Rockwell R	102 - 120	-----	-----	ASTM D785
Izod Impact Strength, Notched	36.96 – 37.04	J/m	at 23°C,	ASTM D256
Tensile Elongation at Yield	10 - 12	%	-----	ASTM D638
Tensile Strength at Yield	30 - 40	MPa	-----	ASTM D638
Heat Deflection Temperature	87 - 103	°C	At 0.46 MPa	ASTM D648
Vicat Softening Point	150 - 158	°C	9.8 N	ASTM D1525

- Manufacturer: Navid zar shimi Pet.co.
- Application: Outdoor use, food containers, auto parts, home appliances.
- Process: Injection Molding.
- Features: Good rigidity, food contact grade, good processability.

**PETRO BAMDAD AZARAN**  
ENGINEERING & TRADING CO

Add: No.148, Motahari St., Tehran, Iran -- Tel: +98 21 87700799 -- Email/Web:  
info@petrobam.com/www.petrobam.com